



Woodworm Free 130

Wood solidifying agent, water-based, protects the wood against mould and insect infestation by physical-mechanical reactions.

Also suitable for porous wood.

Application range:

Preventive breathable wood solidifier, protects the wood against mould and insect infestation by physical-mechanical reactions, also for wood work within roofed exterior areas and woodwork used in damp and humid rooms.

Technical qualities:

Preventive against mould and insect infestation, water vapour permeable. Also suitable for the restoration (solidification) of old wood. Very effective in disguising wood-work against woodworm and insects etc.

Colour:

Colourless, slightly yellow.

Full declaration:

Water, aluminium oxide, silicic acid, potassium palmitate, magnesium oxide, potassium chloride, fatty acids. This product contains max. 1 g/l VOC. EU limit value for this product (cat. a): 30 g/l (2010)

Application:

Applied by brush or spraying: approx. 100 ml/m² per coat. At least two coats necessary! Applied by dipping: Approx. 15 litre/m³. The ambient and surface temperature must be higher than +15°C.

Drying time:

At 20°C and 50% relative humidity: Subsequent treatment after approx. 24 hours, when the wood is completely dried.

Container sizes and coverage:

Application by brush or spray: approx. 100 ml/m² per coat. At least two coats are necessary! Dipping respectively steeping: approx. 15 l/m³.

Sizes	Coverage...*
1l	10 m ²
2,5l	25 m ²
10l	100 m ²
20l	200 m ²

* Coverage per coat

Storage:

Under cool and dry conditions, prevent from freezing. Shelf life of unopened containers nearly 5 years.

Disposal:

According to locally regulated laws. European Waste Catalogue (EWC) 08 01 20.

Precautionary statements:

Safety data sheet available on request.



Keep out of reach of children.
Avoid release to the environment.
Dispose of contents/container according to local regulations.

To achieve optimum results, please refer to the Technical Data Sheets of all products used. The information is based on our current knowledge and experience. However, they do not constitute a guarantee of product properties and do not establish a contractual legal relationship. With the publication of this Technical Data Sheet, all previous information becomes invalid.

Status: January 21, 2025

LEINOS • Reincke Naturfarben GmbH • Industriestraße 3 • 21640 Horneburg, Germany
Tel. +49 (0) 41 63 - 86 74 7-0 • www.LEINOS.de • info@LEINOS.de